

EYLUL

COMPOSITION(iÇERİK): _____ %93 PES %7 OTH.

WEIGHT(Gramaj)(g/m²): _____ 265±%5

MARTINDALE(Aşınma): _____ 8.000

SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.20mm/weft:2.06mm

TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:49.31N /weft:95.75N

TENSILE STRENGTH: _____ warp:1137.0N/weft:2106.63N

PILLING: _____ 3-4@5000revs

USAGE



CLEANING

