

JAGUAR

COMPOSITION(iÇERİK): _____ %95 PES %5 OTH.
WEIGHT(Gramaj)(g/m²): _____ 335±%5
MARTINDALE(Aşınma): _____ 10.000
SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.24mm/weft:2.60mm
TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:117.52N /weft:25.74N
TENSILE STRENGTH: _____ warp:2321.40N/weft:380.24N
PILLING: _____ 4-5@5000revs

USAGE



CLEANING

