



KACAR
TEXTILE


Since 1945

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
18.HTR.51433 HOHENSTEIN HTTI
Tested for harmful substances.
www.oeko-tex.com/standard100

RIVA

COMPOSITION(iÇERİK):	%13 CV %71 PES %16 PP
WEIGHT(Gramaj)(g/m²):	350±%5
MARTINDALE(Aşınma):	35.000
SEAM SLIPPAGE(Dikiş Testi):	warp:3.55mm/weft:3.90mm
TEAR STRENGTH(Yırtılma Mukavemeti):	warp: 155.94N /weft: 131.14N
TENSILE STRENGTH:	warp: 2234.56N/weft: 1174.65N
PILLING:	4-5@5000revs

USAGE



CLEANING

